

General Solid Carbide Milling Guide

Fractional

Type	Rc Hardness	MILLING SFM (Vc)					CHIPLOAD PER TOOTH (Fz)				
		2 flute stub / std.	2 flute extra length	3 & 4 flute stub / std.	3 & 4 flute extra length	Diamond Coated	1/32" - 1/8"	1/8" - 1/4"	1/4" - 1/2"	1/2" - 1"	1" - 1-1/4"
COBALT BASE ALLOYS											
Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 35	-	-	175 - 225	150 - 200	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	125 - 175	100 - 150	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
NICKEL BASE ALLOYS											
Invar, Kovar, Inconel-625/718, Waspalloy, Rene, Hastalloy, A286	< 35	-	-	125 - 175	100 - 150	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	70 - 115	70 - 100	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
IRON BASE ALLOYS											
Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 35	-	-	175 - 225	150 - 200	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	125 - 175	100 - 150	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
MONEL											
Monel - 65% Nickel		175 - 300	125 - 175	175 - 300	125 - 175	-	.0007" - .0015"	.0010" - .0025"	.0015" - .0040"	.0030" - .0050"	.0040" - .0060"
TITANIUM ALLOYS											
Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		200 - 300	125 - 250	200 - 300	125 - 250	-	.0007" - .0015"	.0010" - .0025"	.0015" - .0040"	.0030" - .0050"	.0040" - .0060"
		-	-	175 - 225	150 - 200	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
STAINLESS STEELS											
13/8, 15/5, 17-4, pH Types	< 35	-	-	150 - 250	100 - 150	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	125 - 175	80 - 150	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
Inox, 200 Series, 300 Series	< 35	-	-	200 - 250	125 - 175	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	150 - 200	100 - 150	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
304L, 316L, Nitronic 50, Inox	< 35	-	-	90 - 125	80 - 120	-	.0005" - .0008"	.0008" - .0015"	.0010" - .0020"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	75 - 110	60 - 90	-	.0003" - .0005"	.0005" - .0010"	.0010" - .0015"	.0010" - .0030"	.0020" - .0040"
400 Series	< 35	-	-	150 - 250	100 - 150	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	> 35	-	-	125 - 175	80 - 150	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
HIGH STRENGTH TOOL STEELS											
4140, 4340, 6150, 5210, A2, D2, P20, H11, H13, S2, O1	< 30	-	-	150 - 225	125 - 175	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
	30 - 38	-	-	90 - 125	80 - 120	-	.0003" - .0005"	.0005" - .0015"	.0010" - .0020"	.0010" - .0030"	.0020" - .0040"
	> 38	-	-	60 - 90	50 - 80	-	.0001" - .0003"	.0003" - .0007"	.0008" - .0015"	.0010" - .0025"	.0015" - .0035"
MEDIUM ALLOY TOOL STEELS											
200, 250, 300	< 35	-	-	175 - 250	150 - 200	-	.0007" - .0015"	.0010" - .0025"	.0015" - .0040"	.0030" - .0050"	.0040" - .0060"
	> 35	-	-	100 - 175	100 - 150	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
CARBON STEELS											
Platinum, A36, 1000's, 1100's, 1300's	< 35	-	-	175 - 250	150 - 200	-	.0007" - .0015"	.0010" - .0025"	.0015" - .0040"	.0030" - .0050"	.0040" - .0060"
	> 35	-	-	100 - 175	100 - 150	-	.0005" - .0010"	.0008" - .0020"	.0010" - .0030"	.0020" - .0040"	.0030" - .0050"
CAST MATERIAL											
Steel		225 - 325	175 - 250	250 - 350	175 - 250	-	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"
Ductile Iron		225 - 325	175 - 250	250 - 350	175 - 250	-	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"
Gray Iron		225 - 325	175 - 250	250 - 350	175 - 250	-	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"
Aluminum		250 - 350	250 - 350	250 - 350	250 - 350	-	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"
ALUMINUM											
Aircraft Grade (6061, 7075)	Standard Speed	300 - 500	300 - 500	300 - 500	300 - 500	-	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0150"
	High Speed	(SEE HIGH SPEED ALUMINUM CHART - PAGE 172)									
MAGNESIUM											
		300 - 500	300 - 500	300 - 500	300 - 500	-	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"
COPPER											
Copper Alloys		300 - 400	250 - 350	300 - 450	250 - 350	-	.0007" - .0015"	.0010" - .0025"	.0015" - .0035"	.0020" - .0080"	.0040" - .0100"
BRASS, BRONZE											
Brass, Aluminum/Bronze, Low Silicon Bronze		300 - 400	200 - 300	275 - 375	200 - 300	-	.0007" - .0015"	.0010" - .0025"	.0015" - .0035"	.0020" - .0080"	.0040" - .0100"
COMPOSITE MATERIAL											
Glass Epoxy, Fiberglass, Plastics		200 - 400	200 - 400	200 - 400	200 - 400	200 - 500	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"
Graphite, G10		(SEE GRAPHITE CHART - PAGE 174)				300 - 1000	.0010" - .0020"	.0015" - .0040"	.0020" - .0060"	.0030" - .0100"	.0050" - .0100"

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.

General Solid Carbide Milling Guide

Metric

TECHNICAL

Type	Rc Hardness	MILLING M/Min. (Vc)					CHIPLOAD PER TOOTH (Fz)				
		2 flute stub / std.	2 flute extra length	3 & 4 flute stub / std.	3 & 4 flute extra length	DIAMOND COATED	1.0 - 3.0	3.0 - 6.0	6.0 - 12.0	12.0 - 25.0	25.0 - 32.0
COBALT BASE ALLOYS											
Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 35	-	-	50 - 70	45 - 60	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	> 35	-	-	35 - 50	30 - 45	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
NICKEL BASE ALLOYS											
Invar, Kovar, Inconel-625/718, Waspalloy, Rene, Hastalloy, A286	< 35	-	-	35 - 50	30 - 45	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	> 35	-	-	20 - 35	15 - 25	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
IRON BASE ALLOYS											
Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 35	-	-	50 - 70	45 - 60	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	> 35	-	-	35 - 50	30 - 45	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
MONEL											
Monel - 65% Nickel		50 - 90	35 - 50	50 - 90	35 - 50	-	.015 - .035	.025 - .065	.035 - .100	.075 - .125	.100 - .150
TITANIUM ALLOYS											
Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		60 - 90	35 - 75	60 - 90	35 - 75	-	.015 - .035	.025 - .065	.035 - .100	.075 - .125	.100 - .150
		-	-	50 - 65	45 - 60	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
STAINLESS STEELS											
13/8, 15/5, 17-4, pH Types	< 35	-	-	45 - 75	30 - 45	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	> 35	-	-	35 - 50	25 - 45	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
Inox, 200 Series, 300 Series	< 35	-	-	60 - 80	40 - 55	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	> 35	-	-	45 - 60	30 - 45	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
304L, 316L, Nitronic 50, Inox	< 35	-	-	25 - 40	25 - 35	-	.010 - .020	.020 - .035	.025 - .050	.035 - .075	.050 - .100
	> 35	-	-	20 - 35	15 - 25	-	.005 - .015	.010 - .025	.025 - .035	.025 - .050	.035 - .075
400 Series	< 35	-	-	45 - 75	30 - 45	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	> 35	-	-	35 - 50	25 - 40	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
HIGH STRENGTH TOOL STEELS											
4140, 4340, 6150, 5210, A2, D2, P20, H11, H13, S2, O1	< 30	-	-	45 - 60	35 - 50	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
	30 - 38	-	-	30 - 45	25 - 35	-	.005 - .015	.010 - .035	.025 - .050	.025 - .075	.050 - .100
	> 38	-	-	15 - 30	10 - 25	-	.003 - .008	.005 - .020	.015 - .040	.020 - .065	.035 - .090
MEDIUM ALLOY TOOL STEELS											
200, 250, 300	< 35	-	-	55 - 75	45 - 60	-	.015 - .035	.025 - .065	.035 - .100	.075 - .125	.100 - .150
	> 35	-	-	35 - 55	30 - 45	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
CARBON STEELS											
Platinum, A36, 1000's, 1100's, 1300's	< 35	-	-	55 - 75	45 - 60	-	.015 - .035	.025 - .065	.035 - .100	.075 - .125	.100 - .150
	> 35	-	-	35 - 55	30 - 45	-	.010 - .025	.020 - .050	.025 - .075	.050 - .100	.075 - .125
CAST MATERIAL											
Steel		70 - 100	50 - 75	75 - 105	50 - 75	-	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250
Ductile Iron		75 - 105	60 - 90	90 - 120	60 - 90	-	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250
Gray Iron		70 - 100	50 - 75	75 - 105	50 - 75	-	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250
Aluminum		75 - 105	75 - 105	75 - 105	75 - 105	-	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250
ALUMINUM											
Aircraft Grade (6061, 7075)	Standard Speed	90 - 150	90 - 150	90 - 150	90 - 150	-	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .300
	High Speed	(SEE HIGH SPEED ALUMINUM CHART - PAGE 172)									
MAGNESIUM											
		90 - 150	90 - 150	90 - 150	90 - 150	-	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250
COPPER											
Copper Alloys		120 - 150	75 - 105	90 - 135	75 - 105	-	.020 - .040	.025 - .065	.040 - .090	.050 - .200	.075 - .250
BRASS, BRONZE											
Brass, Aluminum/Bronze, Low Silicon Bronze		90 - 120	60 - 90	75 - 115	60 - 90	-	.020 - .040	.025 - .065	.040 - .090	.050 - .200	.075 - .250
COMPOSITE MATERIAL											
Glass Epoxy, Fiberglass, Plastics		60 - 120	60 - 120	60 - 120	60 - 120	60 - 150	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250
Graphite, G10		(SEE GRAPHITE CHART - PAGE 174)				90 - 300	.025 - .050	.035 - .100	.050 - .150	.075 - .250	.125 - .250

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.